



SPECIFICATION AND COA

PRODUCT NAME: ECOPOL-300

CHEMICAL AND PHYSICAL PROPERTIES:

	SPECIFICATIONS	RESULTS
1% VISCOSITY*	1.0 HOUR 300-600 cps	550
% MOISTURE	4-12	8.0
ASH	1% MAXIMUM	0.6
PROTEIN	10% MAXIMUM	4.5
pH	5-7.5	6.5
CARBOHYDRATE	66% MINIMUM	>84
HEAVY METALS	20 PPM	<10 PPM
LEAD	10 PPM	<5 PPM
ARSENIC	3 PPM	<1 PPM
ACID INSOLUBLE	7.0 % MAXIMUM	<2.0
STARCH	NONE	NONE
ORGANIC VOLATILE	NONE	NONE

BACTERIOLOGICAL SPECIFICATIONS:

AEROBIC PLATE COUNT	5000 MAXIMUM	800
MOLD AND YEAST	500 MAXIMUM	86
COLIFORM/G	NEGATIVE	-VE
SALMONELLA	NEGATIVE	-VE
E. COLI	NEGATIVE	-VE

*1% Viscosity was determined by Brookfield viscometer at 78⁰ F, 20 rpm, and spindle # 1